

常州联拓复合材料有限公司

CHANGZHOU UTEK COMPOSITE CO., LTD.

FuhanYuan 1-812, New North District, Changzhou 213022, Jiangsu, China
 T: 86-519-85856360; www.utekcomposite.com; info@utekcomposite.com

ASSEMBLED ROVING FOR SPRAY-UP

872S Assembled Panel Roving is coated with a silane-based sizing compatible with unsaturated polyester and acrylic resins. 872S is designed for use in semi-transparent, translucent, and opaque panel applications. 872S has excellent resin wet-out and wet-through, and superior chopped dispersion even under low tension.



Product Features

- ◎ Excellent choppability
- ◎ Outstanding dispersion under low tension
- ◎ Low levels of static and fuzz
- ◎ Consistent and uniform laydown
- ◎ Excellent wet-out, similarity between resin and glassfiber refractive indexes
- ◎ Excellent mechanical properties of the finished product

Identification :

Example	E6R12-2400-872S
Glass Type	E6
Assembled Roving	R
Filament Diameter(μm)	12
Linear Density(tex)	2400
Size Code	872S

Technical Parameters

Linear Density (%)	Moisture Content (%)	Size Content (%)	Stiffness (mm)
ISO 1889	ISO 3344	ISO 1887	ISO 3375
± 4	≤ 0.10	0.60 ± 0.15	125±20

Packaging

The product can be packed on pallet or in small cardboard boxes.

Package height mm (in)	260 (10.2)	260 (10.2)
Package inside diameter mm (in)	100 (3.9)	100 (3.9)
Package outside diameter mm (in)	270 (10.6)	310 (12.2)
Package weight kg (lb)	17.5 (37.5)	22 (48.5)

Number of layers	3	4	3	4
Number of doffs per layer	16		12	
Number of doffs per pallet	48	64	36	48
Net weight per pallet kg (lb)	816 (1799)	1088 (2399)	792 (1746)	1056 (2328)

Pallet length mm (in)	1120 (44.1)		1270 (50)	
Pallet width mm (in)	1120 (44.1)		960 (37.8)	
Pallet height mm (in)	940 (37)	1200 (47.2)	940 (37)	1200 (47.2)

Storage

Unless otherwise specified, the fiberglass products should be stored in a dry, cool and moisture-proof area. The fiberglass products should remain in their original package until prior to use. The room temperature and humidity should be always maintained at -10℃~35℃ and ≤80% respectively. To ensure safety and avoid damage to the product, the pallets should not be stacked more than three layers high. When the pallets are stacked in 2 or 3 layers, special care should be taken to correctly and smoothly move the top pallet.

